



Product Data Sheet

C1375

C1375 is a water-base contact adhesive. When sprayed, C1375 provides immediate green strength and bonding properties typically found only in solvent-based contact adhesives.

C1375's superior bonding properties do not require any forced air-drying equipment. There is no premixing of various components, thus eliminating pot life concerns. The immediate bonding properties provide excellent initial handling strength, which prevents delays in production.

C1375 is an effective contact cement for various porous substrates. Bonds can also be made with one non-porous substrate (wood, metal) to a porous substrate (foam, batting).

Clean up of the adhesive and overspray can be accomplished with a small amount of liquid detergent and water or mineral spirits can also be used.

Flush spray equipment (adhesive portion) only with cool water or a mixture of liquid detergent and cool water. Exhaust liquid detergent and water flush and follow with a clean-water flush.

Product is to be protected from freezing. Storage stability in unopened containers is 6 months.

TYPICAL PROPERTIES

Viscosity:	1250 cPs
Specific Gravity:	1.1
Wt./Gal:	9.13 lbs.
Base:	Synthetic rubber (latex)
Solubility in Water:	Dispersible
Appearance:	Thin, creamy-white liquid
Nonvolatile:	54.7%

Application: Hand-held HVLP spray guns with gravity-feed of the adhesive are to be utilized. Please consult with your preferred equipment supplier to obtain best recommendations that will optimize your specific applications.

Choice Adhesives

666 Redna Terrace Ste 600 2500 Carroll Avenue
Cincinnati, OH 45215 Lynchburg, VA 24501
800-330-5566 434-847-5671
www.choiceadhesivescorp.com
service@choiceadhesivescorp.com

For Industrial Use Only

IMPORTANT: The information contained herein is correct to the best of our knowledge and tests. The recommendations and suggestions contained herein are made without guarantee or representation as to results. We recommend that adequate tests be made by the purchaser to determine if a product is suitable for the intended purpose and use. Our only obligations shall be to replace or pay for any material proved defective by our laboratory within our published shelf life period. Beyond the purchase price of materials supplied by us, we assume no liability for damages of any kind and the user accepts the product "as is" and without any other warranties expressed or implied. The suitability of these products to an intended use shall be solely up to the user.